



Phiroze Sethna Private Limited

Factory
Plot No. 101A Road No. 16 Wagie Industrial Estate Thane 400 604 India
Telephone (91 22) 25822220 25811408 Fax (91 22) 25820837 E-mail phir01@vsnl.net
Website www.phirol.com

Registered Office
1st Floor Royal Insurance Building 14 Jamshedji Tata Road Mumbai 400020 India
Telephone (91 22) 22821521 22821845 Fax (91 22) 22851130 E-mail phir01@bom3.vsnl.net.in

Phirol[®]

Technical Data Sheet

Phirol[®] SP Clear Wax

Grade: CPS

Number : 379 Rev.: 00

Issue Date – Sept. 2010

Description

Phirol SP Clear wax is a petroleum wax based formulation, which is recommended as a temporary protective coating for painted surface. It is ready-to-spray product, which dries to tough waxy film, with excellent water repellence. It helps protect painted surface from scratches, stains and water spotting. The wax film can be easily removed by MTO to reveal paint surface to its original appearance. Application by Gravity Spray Gun.

Technical Data

(Should not be considered
as specifications)

Colour / appearance	: Clear, homogeneous liquid
Density	: 0.82 to 0.86 (g/cc; at 23°C)
Dry matter content	: 40-45 (%)
Viscosity (Brookfield)	: 800-1200 cPs (7/20 RPM)
Drying time (Surface Dry)	: 45-60(minutes)
Recommended DFT	: 35 ± 5 (microns)

Uses

Phirol SP Clear wax is used primarily as a protective coating for painted surface such as automobiles during storage and transit.

Storage:

Store in a cool and dry place. Always keep the lid tightly closed after use.

Precaution:

Contains volatile ingredients and is flammable.

Packing:

20 /200 Litre MS Drum

Note :

It should be appreciated that the above information given here is to the best of our knowledge, true and accurate. However, since conditions under which our products are used are beyond our control, recommendations are made without warranty or guarantee.