



Phiroze Sethna Private Limited

Factory

Plot No. 101A Road No. 16 Wagle Industrial Estate Thane 400 604 India
Telephone (91 22) 25822220 25811408 Fax (91 22) 25820837 E-mail phiol101@vsnl.net
Website www.phiol.com

Registered Office

1st Floor Royal Insurance Building 14 Jamshedji Tata Road Mumbai 400020 India
Telephone (91 22) 22821521 22821845 Fax (91 22) 22851130 E-mail phiol@bom3.vsnl.net.in

Phiol®

(Technical Data Sheet)

Phiol® Airdrying Sealer

Grade : ADS

Number : 382 Rev.:00

Issue Date : Aug 11

Description :

Phiol Airdrying Sealer is a one component air drying sealer developed for sealing joints and gaps in automobile bodies.

It is ideally suited for bus body and coach builders who do not have baking facility. It can also be used by OEM's for patch work on painted chassis.

Typical properties:

(Should not be considered as specifications)

Colour,appearance	: White, homogeneous paste
Viscosity	: As per agreement with customers.
Adhesion	: Cohesive break
Solid content	: 60% minimum
Consistency	: Paste
Specific Gravity	: 1.7 max.
Surface Dry	: 30 minutes
Tack free	: 3-4 hrs
Hard Dry	: 48 hrs (2 -3 mm thickness)

Application :

Phiol ADS Sealer can be applied on joints by Gun, Spatula or Brush.

Storage :

To be stored indoors, away from direct sunlight, heat source and moisture.

Shelf Life

Six months under above conditions (in MS Drum)

Packing:

25 kg MS Drum, 420 gm cartridge.

Note :

It should be appreciated that the above information given here is to the best of our knowledge, true and accurate. However, since conditions under which our products are used are beyond our control, recommendations are made without warranty or guarantee.

(An ISO 9001:2008 certified company)